


BZ_01_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\BZ_01_SV_14_PRECRUSH\BZ_01_SV_14_PRECRUSH131.rdf
 Task file: C:\CamsizerXT\CAMSYS\BZ_01_SV_14_PRECRUSH.afg
 Time: 6/12/2015 , 13:00 , duration 6 min 37 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 6064257 , CCD-Z = 55374
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		17.9	100.0	0.756	0.873	0.680	1276
#20	#16	15.0	82.1	0.751	0.869	0.646	2992
#30	#20	11.5	67.1	0.770	0.868	0.655	6273
#40	#30	9.1	55.6	0.797	0.868	0.671	14816
#50	#40	13.1	46.5	0.856	0.882	0.714	68687
#60	#50	10.3	33.4	0.886	0.894	0.725	110164
#70	#60	8.3	23.1	0.893	0.897	0.716	145924
#140	#70	13.4	14.8	0.878	0.895	0.691	655839
PAN	#140	1.4	1.4	0.793	0.897	0.607	18507037



Characteristics

Q3 [%]	x [μm]
10.0	187.2
50.0	486.4
90.0	1401.2
SPAN3 = 2.496	
U3 = 3.712	
Mv3(x) = 663.9 μm	
Sigma3(x) = 484.0 μm	

Mean value SPHT3 = 0.807
 Mean value Symm3 = 0.879
 Mean value b/l3 = 0.665
 Mean value RDNS_C3 = 0.277
 Mean value SPHT_K3 = 0.531

User