


C72_1_5KCRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\C72_1_5KCRUSH\C72_1_5KCRUSH134.rdf
 Task file: C:\CamsizerXT\CAMSYS\C72_1_5KCRUSH.afg
 Time: 12/11/2015 , 13:56 , duration 26 min 56 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 8892525 , CCD-Z = 161475
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.749	0.845	0.659	2
#40	#30	0.0	100.0				0
#50	#40	0.0	100.0	0.831	0.843	0.718	13
#60	#50	0.1	100.0	0.837	0.845	0.782	382
#70	#60	1.2	99.9	0.897	0.883	0.788	10982
#140	#70	77.1	98.7	0.904	0.908	0.753	2960504
PAN	#140	21.6	21.6	0.880	0.926	0.713	34556638



Characteristics

Q3 [%]	x [μm]
10.0	91.6
50.0	127.4
90.0	175.2
SPAN3 =	0.656
U3 =	1.474
Mv3(x) =	130.7 μm
Sigma3(x) =	33.3 μm

Mean value SPHT3 = 0.893
 Mean value Symm3 = 0.910
 Mean value b/l3 = 0.729
 Mean value RDNS_C3 = 0.668
 Mean value SPHT_K3 = 0.652

User