


C75_01_5KCRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\C75_01_5KCRUSH\C75_01_5KCRUSH172.rdf
 Task file: C:\CamsizerXT\CAMSYS\C75_01_5KCRUSH.afg
 Time: 12/22/2015 , 13:50 , duration 22 min 15 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 51587164 , CCD-Z = 729699
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.760	0.818	0.658	4
#40	#30	6.5	100.0	0.897	0.897	0.786	17193
#50	#40	48.5	93.5	0.911	0.908	0.760	265125
#60	#50	22.9	45.0	0.912	0.909	0.742	252461
#70	#60	10.7	22.1	0.909	0.907	0.724	182492
#140	#70	8.1	11.4	0.888	0.898	0.699	422115
PAN	#140	3.3	3.3	0.870	0.908	0.711	75240879



Characteristics

Q3 [%]	x [μm]
10.0	202.9
50.0	310.0
90.0	409.7
SPAN3 = 0.667	
U3 = 1.628	
Mv3(x) = 305.2 μm	
Sigma3(x) = 86.7 μm	

Mean value SPHT3 = 0.902
 Mean value Symm3 = 0.905
 Mean value b/l3 = 0.734
 Mean value RDNS_C3 = 0.604
 Mean value SPHT_K3 = 0.672

User