


C76_1_7KCRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\C76_1_7KCRUSH\C76_1_7KCRUSH134.rdf
 Task file: C:\CamsizerXT\CAMSYS\C76_1_7KCRUSH.afg
 Time: 11/5/2015, 14:12, duration 37 min 35 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 82144493, CCD-Z = 1272709
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.714	0.816	0.742	6
#50	#40	0.1	100.0	0.730	0.796	0.728	336
#60	#50	0.4	99.9	0.828	0.840	0.757	4164
#70	#60	4.2	99.5	0.897	0.883	0.776	58479
#140	#70	84.8	95.3	0.916	0.908	0.748	3791212
PAN	#140	10.5	10.5	0.887	0.915	0.715	131484432



Characteristics

Q3 [%]	x [μm]
10.0	104.4
50.0	155.1
90.0	197.9
SPAN3 = 0.603	
U3 = 1.573	
Mv3(x) = 151.8 μm	
Sigma3(x) = 40.9 μm	

Mean value SPHT3 = 0.905
 Mean value Symm3 = 0.905
 Mean value b/l3 = 0.730
 Mean value RDNS_C3 = 0.656
 Mean value SPHT_K3 = 0.659

User