


C77_01_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\C77_01_PRECRUSH\C77_01_PRECRUSH084.rdf
 Task file: C:\CamsizerXT\CAMSYS\C77_01_PRECRUSH.afg
 Time: 11/23/2015 , 13:15 , duration 10 min 20 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 3719976 , CCD-Z = 90645
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		2.3	100.0	0.761	0.891	0.760	89
#20	#16	3.1	97.7	0.758	0.886	0.740	329
#30	#20	3.9	94.6	0.777	0.881	0.741	1144
#40	#30	4.0	90.7	0.793	0.870	0.738	3206
#50	#40	4.6	86.7	0.815	0.858	0.733	10962
#60	#50	4.1	82.1	0.841	0.857	0.733	20170
#70	#60	7.8	78.0	0.882	0.877	0.748	66459
#140	#70	67.3	70.2	0.908	0.905	0.734	1689623
PAN	#140	2.9	2.9	0.875	0.923	0.686	13456617



Mean value SPHT3 = 0.875
 Mean value Symm3 = 0.895
 Mean value b/l3 = 0.721
 Mean value RDNS_C3 = 0.461
 Mean value SPHT_K3 = 0.647

User