


C77_02_5KCRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\C77_02_5KCRUSH\C77_02_5KCRUSH169.rdf
 Task file: C:\CamsizerXT\CAMSYS\C77_02_5KCRUSH.afg
 Time: 12/22/2015, 13:07, duration 24 min 38 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 35581149, CCD-Z = 890742
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.0	100.0	0.623	0.710	0.719	95
#60	#50	0.4	100.0	0.830	0.837	0.769	2916
#70	#60	4.9	99.6	0.904	0.886	0.784	58663
#140	#70	88.1	94.7	0.916	0.907	0.743	3053552
PAN	#140	6.6	6.6	0.886	0.917	0.708	78654503



Characteristics

Q3 [%]	x [μm]
10.0	116.0
50.0	163.4
90.0	201.2
SPAN3 =	0.522
U3 =	1.472
Mv3(x) =	159.6 μm
Sigma3(x) =	36.6 μm

Mean value SPHT3 = 0.907
 Mean value Symm3 = 0.905
 Mean value b/l3 = 0.728
 Mean value RDNS_C3 = 0.661
 Mean value SPHT_K3 = 0.653

User