


C77_03_5KCRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\C77_03_5KCRUSH\C77_03_5KCRUSH153.rdf
 Task file: C:\CamsizerXT\CAMSYS\C77_03_5KCRUSH.afg
 Time: 12/21/2015 , 13:58 , duration 21 min 28 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 28422311 , CCD-Z = 661826
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.1	100.0	0.675	0.726	0.732	279
#60	#50	1.4	99.9	0.883	0.873	0.774	12938
#70	#60	13.7	98.5	0.923	0.903	0.775	190572
#140	#70	80.4	84.8	0.919	0.910	0.741	2970790
PAN	#140	4.4	4.4	0.876	0.915	0.700	66757867



Characteristics

Q3 [%]	x [μm]
10.0	124.7
50.0	175.2
90.0	220.5
SPAN3 =	0.547
U3 =	1.480
Mv3(x) =	173.0 μm
Sigma3(x) =	39.6 μm

Mean value SPHT3 = 0.911
 Mean value Symm3 = 0.907
 Mean value b/l3 = 0.729
 Mean value RDNS_C3 = 0.662
 Mean value SPHT_K3 = 0.654

User