


C77_1_5KCRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\C77_1_5KCRUSH\C77_1_5KCRUSH131.rdf
 Task file: C:\CamsizerXT\CAMSYS\C77_1_5KCRUSH.afg
 Time: 12/3/2015 , 15:15 , duration 28 min 25 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 23788934 , CCD-Z = 478688
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.0	100.0	0.669	0.753	0.720	36
#60	#50	0.3	100.0	0.819	0.830	0.769	1165
#70	#60	3.8	99.7	0.905	0.887	0.787	29700
#140	#70	87.3	95.9	0.917	0.908	0.746	1953633
PAN	#140	8.6	8.6	0.884	0.916	0.707	58716684



Mean value SPHT3 = 0.908
 Mean value Symm3 = 0.906
 Mean value b/l3 = 0.730
 Mean value RDNS_C3 = 0.652
 Mean value SPHT_K3 = 0.657

User