


C82_02_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\C82_02_PRECRUSH\C82_02_PRECRUSH080.rdf
 Task file: C:\CamsizerXT\CAMSYS\C82_02_PRECRUSH.afg
 Time: 9/17/2015 , 17:23 , duration 11 min 12 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 6106669 , CCD-Z = 179100
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.9	100.0	0.663	0.858	0.743	30
#20	#16	0.6	99.1	0.685	0.867	0.664	52
#30	#20	0.5	98.5	0.719	0.867	0.662	136
#40	#30	0.8	98.0	0.765	0.855	0.724	626
#50	#40	3.2	97.2	0.837	0.862	0.752	8743
#60	#50	7.7	94.0	0.886	0.882	0.758	40307
#70	#60	16.3	86.3	0.909	0.896	0.755	138050
#140	#70	66.1	70.0	0.906	0.904	0.730	1703224
PAN	#140	3.9	3.9	0.877	0.924	0.695	20166797



Characteristics

Q3 [%]	x [μm]
10.0	122.9
50.0	183.6
90.0	266.7
SPAN3 =	0.783
U3 =	1.603
Mv3(x) =	208.6 μm
Sigma3(x) =	158.2 μm

Mean value SPHT3 = 0.889
 Mean value Symm3 = 0.898
 Mean value b/l3 = 0.719
 Mean value RDNS_C3 = 0.574
 Mean value SPHT_K3 = 0.638

User