


C82_03_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\C82_03_PRECRUSH\C82_03_PRECRUSH083.rdf
 Task file: C:\CamsizerXT\CAMSYS\C82_03_PRECRUSH.afg
 Time: 10/29/2015 , 15:39 , duration 13 min 41 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 2094512 , CCD-Z = 37712
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0	0.494	0.819	0.782	1
#20	#16	0.1	100.0	0.821	0.906	0.779	4
#30	#20	0.2	99.9	0.797	0.881	0.778	69
#40	#30	0.7	99.7	0.811	0.871	0.756	563
#50	#40	5.0	99.0	0.860	0.873	0.758	11989
#60	#50	11.7	94.0	0.897	0.890	0.757	52826
#70	#60	18.5	82.3	0.909	0.897	0.745	130470
#140	#70	61.0	63.8	0.902	0.903	0.725	1356694
PAN	#140	2.8	2.8	0.873	0.917	0.676	3452162



Characteristics

Q3 [%]	x [μm]
10.0	125.8
50.0	190.5
90.0	276.2
SPAN3 = 0.789	
U3 = 1.637	
Mv3(x) = 199.4 μm	
Sigma3(x) = 70.4 μm	

Mean value SPHT3 = 0.891
 Mean value Symm3 = 0.897
 Mean value b/l3 = 0.717
 Mean value RDNS_C3 = 0.597
 Mean value SPHT_K3 = 0.630

User