


C83_01_5KCRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\C83_01_5KCRUSH\C83_01_5KCRUSH072.rdf
 Task file: C:\CamsizerXT\CAMSYS\C83_01_5KCRUSH.afg
 Time: 1/11/2016 , 13:15 , duration 29 min 52 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 184783352 , CCD-Z = 2031617
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.1	100.0	0.510	0.848	0.767	2
#20	#16	0.1	99.9	0.671	0.859	0.704	13
#30	#20	0.3	99.8	0.705	0.844	0.697	108
#40	#30	0.5	99.5	0.749	0.849	0.711	526
#50	#40	1.1	99.0	0.791	0.845	0.722	3362
#60	#50	1.7	97.9	0.849	0.864	0.743	10466
#70	#60	7.7	96.2	0.908	0.897	0.766	81916
#140	#70	66.4	88.5	0.918	0.910	0.752	2561334
PAN	#140	22.1	22.1	0.900	0.915	0.750	346733965



Characteristics

Q3 [%]	x [μm]
10.0	46.6
50.0	144.2
90.0	216.5
SPAN3 =	1.178
U3 =	3.424
Mv3(x) =	148.3 μm
Sigma3(x) =	93.7 μm

Mean value SPHT3 = 0.903
 Mean value Symm3 = 0.907
 Mean value b/l3 = 0.738
 Mean value RDNS_C3 = 0.661
 Mean value SPHT_K3 = 0.678

User