


C84_01_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\C84_01_PRECRUSH\C84_01_PRECRUSH158.rdf
 Task file: C:\CamsizerXT\CAMSYS\C84_01_PRECRUSH.afg
 Time: 12/21/2015 , 15:33 , duration 11 min 20 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 8372828 , CCD-Z = 187982
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		1.3	100.0	0.687	0.867	0.696	53
#20	#16	1.6	98.7	0.756	0.886	0.726	183
#30	#20	1.5	97.1	0.757	0.871	0.725	476
#40	#30	2.0	95.6	0.791	0.866	0.734	1864
#50	#40	4.6	93.6	0.824	0.858	0.739	12659
#60	#50	6.7	89.0	0.866	0.871	0.744	38063
#70	#60	14.4	82.3	0.899	0.890	0.749	133360
#140	#70	64.6	67.9	0.906	0.904	0.726	1672582
PAN	#140	3.3	3.3	0.881	0.923	0.705	18906758



Characteristics

Q3 [%]	x [μm]
10.0	129.0
50.0	187.1
90.0	314.8
SPAN3 = 0.993	
U3 = 1.550	
Mv3(x) = 232.9 μm	
Sigma3(x) = 191.8 μm	

Mean value SPHT3 = 0.881
 Mean value Symm3 = 0.895
 Mean value b/l3 = 0.714
 Mean value RDNS_C3 = 0.505
 Mean value SPHT_K3 = 0.628

User