


CFD\_08\_SV\_14\_PRECRUSH

Company:  
 User:  
 Result file: C:\CamsizerXT\CAMDAT\CFD\_08\_SV\_14\_PRECRUSH\CFD\_08\_SV\_14\_PRECRUSH076.rdf  
 Task file: C:\CamsizerXT\CAMSYS\CFD\_08\_SV\_14\_PRECRUSH.afg  
 Time: 6/24/2015 , 13:58 , duration 10 min 42 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc\_min  
 No. of particles: CCD-B = 1154180 , CCD-Z = 16975  
 Velocity adaption: no  
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		13.0	100.0	0.710	0.865	0.618	96
#20	#16	10.0	87.0	0.756	0.862	0.642	250
#30	#20	14.0	77.0	0.780	0.871	0.659	957
#40	#30	13.0	63.0	0.807	0.871	0.676	2648
#50	#40	15.6	50.0	0.856	0.884	0.705	9527
#60	#50	9.4	34.4	0.883	0.894	0.719	11956
#70	#60	7.0	25.0	0.892	0.897	0.717	15258
#140	#70	15.3	18.0	0.885	0.899	0.706	109757
PAN	#140	2.7	2.7	0.839	0.906	0.669	3776527



Mean value SPHT3 = 0.813  
 Mean value Symm3 = 0.880  
 Mean value b/l3 = 0.665  
 Mean value RDNS\_C3 = 0.316  
 Mean value SPHT\_K3 = 0.533

User