


CFD\_08\_SV\_14\_SPHERE\_ROUND\_140MESH

Company:  
 User:  
 Result file: C:\...\_08\_SV\_14\_SPHERE\_ROUND\_140MESH\CFD\_08\_SV\_14\_SPHERE\_ROUND\_140MESH074.rdf  
 Task file: C:\CamsizerXT\CAMSYS\CFD\_08\_SV\_14\_SPHERE\_ROUND\_140MESH.afg  
 Time: 8/10/2015, 11:50, duration 8 min 7 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc\_min  
 No. of particles: CCD-B = 3051992, CCD-Z = 85621  
 Velocity adaption: no  
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.415	0.520	0.819	1
#50	#40	0.1	100.0	0.677	0.753	0.710	419
#60	#50	3.3	99.9	0.863	0.870	0.749	16586
#70	#60	18.0	96.6	0.896	0.892	0.745	141920
#140	#70	75.1	78.6	0.886	0.898	0.712	1781705
PAN	#140	3.5	3.5	0.841	0.917	0.626	16302284



Mean value SPHT3 = 0.876  
 Mean value Symm3 = 0.894  
 Mean value b/l3 = 0.696  
 Mean value RDNS\_C3 = 0.542  
 Mean value SPHT\_K3 = 0.585

User