


CFD_17_SV_14_PRECRUSH

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDAT\CFD_17_SV_14_PRECRUSH\CFD_17_SV_14_PRECRUSH053.rdf
Task file:	C:\CamsizerXT\CAMSYS\CFD_17_SV_14_PRECRUSH.afg
Time:	2/23/2015 , 16:36 , duration 7 min 2 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 3225296 , CCD-Z = 52485
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		12.4	100.0	0.727	0.857	0.673	1032
#20	#16	15.6	87.6	0.763	0.862	0.669	3776
#30	#20	21.3	72.0	0.810	0.873	0.692	14305
#40	#30	19.8	50.7	0.840	0.881	0.696	36651
#50	#40	14.6	30.9	0.853	0.885	0.687	73688
#60	#50	5.2	16.3	0.858	0.886	0.678	57715
#70	#60	3.6	11.1	0.864	0.888	0.674	65795
#140	#70	6.5	7.5	0.851	0.889	0.656	376501
PAN	#140	1.0	1.0	0.780	0.898	0.599	12590870



Mean value SPHT3 = 0.802
Mean value Symm3 = 0.874
Mean value b/l3 = 0.661
Mean value RDNS_C3 = 0.309
Mean value SPHT_K3 = 0.525

User