


CFD_18_7kcrush.afg

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\CFD_18_7kcrush.afg\CFD_18_7kcrush.afg051.rdf
 Task file: C:\CamsizerXT\CAMSYS\CFD_18_7kcrush.afg
 Time: 3/5/2015 , 15:21 , duration 28 min 58 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 148522706 , CCD-Z = 660281
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0	0.609	0.821	0.703	9
#30	#20	0.1	100.0	0.638	0.824	0.686	61
#40	#30	0.2	99.9	0.676	0.809	0.699	703
#50	#40	1.3	99.7	0.749	0.816	0.714	10336
#60	#50	2.6	98.4	0.818	0.842	0.726	41025
#70	#60	11.9	95.8	0.893	0.888	0.757	317899
#140	#70	73.6	83.9	0.904	0.902	0.736	5600275
PAN	#140	10.3	10.3	0.832	0.885	0.666	223245004



Mean value SPHT3 = 0.883
 Mean value Symm3 = 0.894
 Mean value b/l3 = 0.715
 Mean value RDNS_C3 = 0.432
 Mean value SPHT_K3 = 0.634

User