


CFD\_18\_SV\_14\_SANDR140

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDAT\CFD_18_SV_14_SANDR140\CFD_18_SV_14_SANDR140056.rdf
Task file:	C:\CamsizerXT\CAMSYS\CFD_18_SV_14_SANDR140.afg
Time:	2/24/2015 , 15:00 , duration 9 min 1 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 2589610 , CCD-Z = 51308
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0	0.809	0.829	0.688	1
#30	#20	0.0	100.0	0.861	0.881	0.612	1
#40	#30	0.0	100.0	0.888	0.914	0.696	3
#50	#40	0.1	100.0	0.650	0.724	0.696	170
#60	#50	1.5	99.9	0.854	0.858	0.758	6821
#70	#60	14.0	98.4	0.907	0.895	0.765	101564
#140	#70	83.4	84.4	0.904	0.906	0.729	1550032
PAN	#140	1.0	1.0	0.839	0.915	0.600	8522888



Mean value SPHT3 = 0.896
Mean value Symm3 = 0.902
Mean value b/l3 = 0.718
Mean value RDNS_C3 = 0.587
Mean value SPHT_K3 = 0.632

User