


CHOT_01_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\CHOT_01_SV_14_PRECRUSH\CHOT_01_SV_14_PRECRUSH158.rdf
 Task file: C:\CamsizerXT\CAMSYS\CHOT_01_SV_14_PRECRUSH.afg
 Time: 6/16/2015 , 13:33 , duration 9 min 53 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 8530740 , CCD-Z = 77594
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		8.4	100.0	0.785	0.886	0.708	486
#20	#16	15.7	91.6	0.796	0.889	0.694	2212
#30	#20	15.9	75.9	0.809	0.888	0.696	6027
#40	#30	12.0	60.0	0.829	0.889	0.706	13133
#50	#40	9.7	48.0	0.851	0.890	0.719	30648
#60	#50	4.4	38.3	0.865	0.889	0.725	31050
#70	#60	3.7	33.9	0.878	0.889	0.731	45223
#140	#70	18.1	30.2	0.884	0.895	0.736	1045368
PAN	#140	12.1	12.1	0.881	0.923	0.730	12808193



Characteristics

Q3 [%]	x [μm]
10.0	99.8
50.0	453.0
90.0	1132.6
SPAN3 = 2.280	
U3 = 6.009	
Mv3(x) = 540.1 μm	
Sigma3(x) = 403.5 μm	

Mean value SPHT3 = 0.833
 Mean value Symm3 = 0.894
 Mean value b/l3 = 0.699
 Mean value RDNS_C3 = 0.409
 Mean value SPHT_K3 = 0.598

User