


C_03_PRECRUSH

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDAT\C_03_PRECRUSH\C_03_PRECRUSH193.rdf
Task file:	C:\CamsizerXT\CAMSYS\C_03_PRECRUSH.afg
Time:	6/26/2015 , 14:29 , duration 9 min 14 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 11102321 , CCD-Z = 136333
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		13.5	100.0	0.785	0.873	0.667	785
#20	#16	16.3	86.5	0.787	0.872	0.655	2812
#30	#20	18.9	70.2	0.797	0.872	0.653	8800
#40	#30	16.9	51.3	0.810	0.875	0.654	21932
#50	#40	13.4	34.4	0.826	0.880	0.653	47862
#60	#50	5.1	21.0	0.838	0.884	0.653	40394
#70	#60	3.6	15.9	0.849	0.887	0.658	48221
#140	#70	8.9	12.3	0.856	0.892	0.668	437776
PAN	#140	3.4	3.4	0.840	0.909	0.679	36828821



Mean value SPHT3 = 0.798
Mean value Symm3 = 0.878
Mean value b/l3 = 0.633
Mean value RDNS_C3 = 0.267
Mean value SPHT_K3 = 0.458

User