


C_04_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\C_04_PRECRUSH\C_04_PRECRUSH195.rdf
 Task file: C:\CamsizerXT\CAMSYS\C_04_PRECRUSH.afg
 Time: 6/26/2015 , 14:50 , duration 18 min 4 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 18394183 , CCD-Z = 148624
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		13.3	100.0	0.736	0.871	0.606	51
#20	#16	10.6	86.7	0.783	0.874	0.667	170
#30	#20	14.3	76.1	0.786	0.873	0.651	604
#40	#30	13.4	61.8	0.801	0.877	0.651	1568
#50	#40	11.6	48.4	0.829	0.882	0.665	3806
#60	#50	4.8	36.8	0.844	0.885	0.676	3608
#70	#60	4.0	32.0	0.857	0.888	0.682	4888
#140	#70	12.0	28.0	0.866	0.891	0.689	58350
PAN	#140	16.0	16.0	0.879	0.903	0.719	45231302



Characteristics

Q3 [%] x [μm]
 10.0 61.2
 50.0 443.3
 90.0 1388.2
 SPAN3 = 2.993
 U3 = 9.374
 Mv3(x) = 610.0 μm
 Sigma3(x) = 586.1 μm

Mean value SPHT3 = 0.808
 Mean value Symm3 = 0.882
 Mean value b/l3 = 0.651
 Mean value RDNS_C3 = 0.293
 Mean value SPHT_K3 = 0.498

User