


C\_07\_PRECRUSH

|                    |   |
|--------------------|---|
| Company:           |   |
| User:              |   |
| Result file:       | C:\CamsizerXT\CAMDAT\C_07_PRECRUSH\C_07_PRECRUSH207.rdf   |
| Task file:         | C:\CamsizerXT\CAMSYS\C_07_PRECRUSH.afg  |
| Time:              | 6/29/2015 , 16:05 , duration 9 min 56 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm |
| Particle model:    | xc_min  |
| No. of particles:  | CCD-B = 36380454 , CCD-Z = 313782   |
| Velocity adaption: | no  |
| Fitting:           | no  |
| Material:          |   |

| ASTM(+) | No(-) | retained [%] | passing [%] | SPHT3 | Symm3 | b/l3  | PDN      |
|---------|-------|--------------|-------------|-------|-------|-------|----------|
| > #16   |       | 24.8         | 100.0       | 0.808 | 0.886 | 0.712 | 903      |
| #20     | #16   | 14.9         | 75.2        | 0.802 | 0.879 | 0.689 | 2090     |
| #30     | #20   | 14.5         | 60.3        | 0.813 | 0.878 | 0.689 | 5509     |
| #40     | #30   | 12.2         | 45.8        | 0.828 | 0.880 | 0.690 | 13209    |
| #50     | #40   | 10.0         | 33.6        | 0.843 | 0.882 | 0.689 | 30387    |
| #60     | #50   | 4.3          | 23.6        | 0.855 | 0.885 | 0.692 | 28089    |
| #70     | #60   | 3.2          | 19.3        | 0.866 | 0.887 | 0.698 | 36997    |
| #140    | #70   | 9.8          | 16.1        | 0.874 | 0.892 | 0.706 | 421493   |
| PAN     | #140  | 6.3          | 6.3         | 0.867 | 0.906 | 0.714 | 56018154 |



|                            |
|----------------------------|
| Mean value SPHT3 = 0.822   |
| Mean value Symm3 = 0.884   |
| Mean value b/l3 = 0.685    |
| Mean value RDNS_C3 = 0.301 |
| Mean value SPHT_K3 = 0.574 |

User