


DBR_01_6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\DBR_01_6K\DBR_01_6K095.rdf
 Task file: C:\CamsizerXT\CAMSYS\DBR_01_6K.afg
 Time: 7/24/2015, 17:09, duration 36 min 28 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 105055391, CCD-Z = 1205
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.5	100.0	0.616	0.893	0.626	7
#20	#16	0.2	99.5	0.672	0.854	0.677	31
#30	#20	0.2	99.3	0.724	0.860	0.675	100
#40	#30	0.4	99.1	0.755	0.854	0.702	445
#50	#40	0.7	98.7	0.804	0.856	0.720	2802
#60	#50	1.1	98.0	0.849	0.867	0.744	8718
#70	#60	4.7	96.9	0.900	0.893	0.767	66110
#140	#70	40.9	92.2	0.918	0.907	0.751	2166745
PAN	#140	51.3	51.3	0.793	0.885	0.700	230456598



Characteristics

Q3 [%]	x [μm]
10.0	38.8
50.0	102.6
90.0	203.2
SPAN3 =	1.603
U3 =	3.315
Mv3(x) =	126.3 μm
Sigma3(x) =	187.6 μm

Mean value SPHT3 = 0.842
 Mean value Symm3 = 0.892
 Mean value b/l3 = 0.718
 Mean value RDNS_C3 = 0.318
 Mean value SPHT_K3 = 0.645

User