


DILL_03_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\DILL_03_SV_14_PRECRUSH\DILL_03_SV_14_PRECRUSH026.rdf
 Task file: C:\CamsizerXT\CAMSYS\DILL_03_SV_14_PRECRUSH.afg
 Time: 2/10/2015, 14:13, duration 15 min 26 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 22983556, CCD-Z = 319390
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		7.4	100.0	0.764	0.890	0.728	435
#20	#16	4.8	92.6	0.768	0.884	0.696	719
#30	#20	3.0	87.8	0.777	0.879	0.702	1293
#40	#30	2.7	84.8	0.804	0.875	0.720	3582
#50	#40	4.8	82.1	0.859	0.881	0.748	20088
#60	#50	5.6	77.3	0.889	0.888	0.754	49078
#70	#60	8.8	71.7	0.906	0.895	0.754	122342
#140	#70	56.9	62.9	0.913	0.909	0.745	2911286
PAN	#140	6.0	6.0	0.892	0.924	0.719	63190605



Characteristics

Q3 [%]	x [μm]
10.0	116.7
50.0	180.9
90.0	1029.9
SPAN3 = 5.047	
U3 = 1.743	
Mv3(x) = 338.4 μm	
Sigma3(x) = 384.9 μm	

Mean value SPHT3 = 0.877
 Mean value Symm3 = 0.900
 Mean value b/l3 = 0.726
 Mean value RDNS_C3 = 0.490
 Mean value SPHT_K3 = 0.657

User