


## DILL\_03\_SV\_14\_SANDR\_140

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDAT\DILL_03_SV_14_SANDR_140\DILL_03_SV_14_SANDR_140024.rdf
Task file:	C:\CamsizerXT\CAMSYS\DILL_03_SV_14_SANDR_140.afg
Time:	2/9/2015 , 16:15 , duration 7 min 5 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 3191183 , CCD-Z = 99318
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.0	100.0	0.638	0.718	0.727	89
#60	#50	1.1	100.0	0.862	0.859	0.769	4431
#70	#60	9.7	98.9	0.908	0.892	0.770	63410
#140	#70	87.1	89.2	0.911	0.908	0.743	1804013
PAN	#140	2.1	2.1	0.896	0.935	0.678	13738505



Mean value SPHT3 = 0.903
Mean value Symm3 = 0.904
Mean value b/l3 = 0.730
Mean value RDNS_C3 = 0.682
Mean value SPHT_K3 = 0.659

\_\_\_\_\_  
User