


DILL\_04\_SV\_14\_PRECRUSH

Company:  
 User:  
 Result file: C:\CamsizerXT\CAMDAT\DILL\_04\_SV\_14\_PRECRUSH\DILL\_04\_SV\_14\_PRECRUSH025.rdf  
 Task file: C:\CamsizerXT\CAMSYS\DILL\_04\_SV\_14\_PRECRUSH.afg  
 Time: 2/10/2015, 14:00, duration 9 min 25 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc\_min  
 No. of particles: CCD-B = 6608362, CCD-Z = 111243  
 Velocity adaption: no  
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.3	100.0	0.708	0.870	0.733	35
#20	#16	4.0	99.7	0.727	0.863	0.717	833
#30	#20	5.3	95.7	0.746	0.855	0.707	2875
#40	#30	7.2	90.4	0.788	0.852	0.716	11319
#50	#40	15.5	83.2	0.863	0.875	0.739	73112
#60	#50	17.5	67.7	0.904	0.898	0.751	169972
#70	#60	21.5	50.2	0.920	0.907	0.752	339960
#140	#70	28.0	28.7	0.912	0.908	0.719	927910
PAN	#140	0.7	0.7	0.856	0.912	0.686	17481091



Mean value SPHT3 = 0.872  
 Mean value Symm3 = 0.890  
 Mean value b/l3 = 0.719  
 Mean value RDNS\_C3 = 0.457  
 Mean value SPHT\_K3 = 0.647

User