


DILL_05_SV_14_CRUSH5K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\DILL_05_SV_14_CRUSH5K\DILL_05_SV_14_CRUSH5K044.rdf
 Task file: C:\CamsizerXT\CAMSYS\DILL_05_SV_14_CRUSH5K.afg
 Time: 2/20/2015, 15:12, duration 36 min 38 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 143771023, CCD-Z = 1871912
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0	0.899	0.927	0.738	1
#30	#20	0.0	100.0	0.627	0.801	0.665	1
#40	#30	0.0	100.0	0.751	0.874	0.708	11
#50	#40	0.1	100.0	0.733	0.814	0.725	452
#60	#50	0.4	99.9	0.830	0.851	0.756	5139
#70	#60	3.0	99.5	0.894	0.885	0.773	60687
#140	#70	74.8	96.5	0.911	0.904	0.754	6728895
PAN	#140	21.7	21.7	0.900	0.920	0.728	328309299



Characteristics

Q3 [%]	x [μm]
10.0	85.7
50.0	129.5
90.0	186.3
SPAN3 =	0.777
U3 =	1.612
Mv3(x) =	132.5 μm
Sigma3(x) =	42.9 μm

Mean value SPHT3 = 0.901
 Mean value Symm3 = 0.905
 Mean value b/l3 = 0.733
 Mean value RDNS_C3 = 0.649
 Mean value SPHT_K3 = 0.667

User