


DILL_03_SV_14_CDILL_05_SV_14_CRUSH6KRUSH6K

Company:
User:
Result file: C:\...DAT\DILL_05_SV_14_CRUSH6K\DILL_03_SV_DILL_05_SV_14_CRUSH6K14_CRUSH6K042.rdf
Task file: C:\CamsizerXT\CAMSYS\DILL_05_SV_14_CRUSH6K.afg
Time: 2/17/2015, 13:23, duration 32 min 12 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
No. of particles: CCD-B = 158489420, CCD-Z = 1765516
Velocity adaption: no
Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0	0.718	0.872	0.556	1
#20	#16	0.0	100.0	0.745	0.913	0.694	1
#30	#20	0.0	100.0	0.800	0.857	0.744	5
#40	#30	0.0	100.0	0.730	0.852	0.686	25
#50	#40	0.2	100.0	0.764	0.829	0.730	781
#60	#50	0.5	99.8	0.826	0.849	0.750	5926
#70	#60	3.3	99.3	0.895	0.886	0.772	57609
#140	#70	71.9	96.0	0.912	0.906	0.755	5552281
PAN	#140	24.1	24.1	0.899	0.920	0.736	314295208



Characteristics

Q3 [%]	x [μm]
10.0	75.9
50.0	129.6
90.0	188.4
SPAN3 =	0.869
U3 =	1.828
Mv3(x) =	131.5 μm
Sigma3(x) =	48.8 μm

Mean value SPHT3 = 0.901
Mean value Symm3 = 0.907
Mean value b/l3 = 0.735
Mean value RDNS_C3 = 0.659
Mean value SPHT_K3 = 0.672

User