


DILL_06_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\DILL_06_SV_14_PRECRUSH\DILL_06_SV_14_PRECRUSH027.rdf
 Task file: C:\CamsizerXT\CAMSYS\DILL_06_SV_14_PRECRUSH.afg
 Time: 2/6/2015 , 10:38 , duration 19 min 25 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 25091930 , CCD-Z = 252716
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0	0.187	0.668	0.635	1
#30	#20	0.0	100.0	0.376	0.674	0.616	15
#40	#30	3.2	100.0	0.808	0.871	0.776	12267
#50	#40	25.3	96.8	0.837	0.880	0.751	188580
#60	#50	12.3	71.5	0.850	0.878	0.741	192319
#70	#60	7.8	59.2	0.862	0.879	0.732	194636
#140	#70	43.1	51.4	0.893	0.895	0.741	5247994
PAN	#140	8.3	8.3	0.865	0.910	0.683	53787489



Characteristics

Q3 [%]	x [μm]
10.0	109.2
50.0	203.3
90.0	382.4
SPAN3 = 1.343	
U3 = 2.320	
Mv3(x) = 226.3 μm	
Sigma3(x) = 106.2 μm	

Mean value SPHT3 = 0.861
 Mean value Symm3 = 0.887
 Mean value b/l3 = 0.726
 Mean value RDNS_C3 = 0.435
 Mean value SPHT_K3 = 0.670

User