


DILL_07_SV_14_CRUSH7k

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\DILL_07_SV_14_CRUSH7k\DILL_07_SV_14_CRUSH7k020.rdf
 Task file: C:\CamsizerXT\CAMSYS\DILL_07_SV_14_CRUSH7k.afg
 Time: 2/2/2015 , 10:29 , duration 22 min 12 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 66461553 , CCD-Z = 628330
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.732	0.840	0.733	3
#50	#40	0.1	100.0	0.697	0.761	0.725	583
#60	#50	1.4	99.9	0.885	0.876	0.777	25214
#70	#60	11.9	98.5	0.921	0.901	0.776	317266
#140	#70	80.0	86.6	0.914	0.907	0.741	6250099
PAN	#140	6.6	6.6	0.867	0.910	0.694	119188296



Characteristics

Q3 [%]	x [μm]
10.0	116.6
50.0	168.2
90.0	218.3
SPAN3 = 0.605	
U3 = 1.530	
Mv3(x) = 166.4 μm	
Sigma3(x) = 42.4 μm	

Mean value SPHT3 = 0.905
 Mean value Symm3 = 0.904
 Mean value b/l3 = 0.727
 Mean value RDNS_C3 = 0.629
 Mean value SPHT_K3 = 0.651

User