


DILL_07_SV_14_CRUSH8k

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\DILL_07_SV_14_CRUSH8k\DILL_07_SV_14_CRUSH8k026.rdf
 Task file: C:\CamsizerXT\CAMSYS\DILL_07_SV_14_CRUSH8k.afg
 Time: 4/22/2015, 8:51, duration 20 min 53 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 17986110, CCD-Z = 282808
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0	0.492	0.862	0.716	2
#30	#20	0.0	100.0	0.278	0.709	0.429	3
#40	#30	0.0	100.0	0.462	0.775	0.580	15
#50	#40	0.1	100.0	0.660	0.760	0.702	340
#60	#50	0.9	99.9	0.872	0.868	0.775	13409
#70	#60	10.2	99.0	0.922	0.902	0.780	238393
#140	#70	79.1	88.8	0.913	0.907	0.746	5678113
PAN	#140	9.7	9.7	0.867	0.915	0.704	48044772



Mean value SPHT3 = 0.903
 Mean value Symm3 = 0.905
 Mean value b/l3 = 0.731
 Mean value RDNS_C3 = 0.627
 Mean value SPHT_K3 = 0.660

User