


DILL_08_SV_14_6K_CRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\DILL_08_SV_14_6K_CRUSH\DILL_08_SV_14_6K_CRUSH046.rdf
 Task file: C:\CamsizerXT\CAMSYS\DILL_08_SV_14_6K_CRUSH.afg
 Time: 3/3/2015, 15:05, duration 31 min 52 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 119254494, CCD-Z = 1064426
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.533	0.849	0.696	1
#40	#30	0.0	100.0	0.699	0.825	0.703	22
#50	#40	0.1	100.0	0.741	0.810	0.733	1002
#60	#50	0.6	99.9	0.807	0.833	0.742	7780
#70	#60	3.7	99.3	0.893	0.883	0.773	87607
#140	#70	84.4	95.6	0.912	0.905	0.751	6627448
PAN	#140	11.2	11.2	0.874	0.909	0.707	167102370



Characteristics

Q3 [%]	x [μm]
10.0	101.4
50.0	151.4
90.0	195.4
SPAN3 = 0.621	
U3 = 1.580	
Mv3(x) = 149.1 μm	
Sigma3(x) = 41.3 μm	

Mean value SPHT3 = 0.900
 Mean value Symm3 = 0.902
 Mean value b/l3 = 0.732
 Mean value RDNS_C3 = 0.619
 Mean value SPHT_K3 = 0.666

User