


DILL_08_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\DILL_08_SV_14_PRECRUSH\DILL_08_SV_14_PRECRUSH045.rdf
 Task file: C:\CamsizerXT\CAMSYS\DILL_08_SV_14_PRECRUSH.afg
 Time: 2/23/2015, 14:06, duration 17 min 18 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 6475616, CCD-Z = 171383
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.0	100.0	0.621	0.705	0.717	97
#60	#50	0.5	100.0	0.828	0.839	0.762	3863
#70	#60	5.0	99.5	0.897	0.883	0.773	66432
#140	#70	92.6	94.5	0.908	0.904	0.741	3765530
PAN	#140	1.9	1.9	0.862	0.923	0.633	33767043



Characteristics

Q3 [%]	x [μm]
10.0	123.8
50.0	159.0
90.0	200.5
SPAN3 =	0.482
U3 =	1.347
Mv3(x) =	160.7 μm
Sigma3(x) =	30.4 μm

Mean value SPHT3 = 0.899
 Mean value Symm3 = 0.901
 Mean value b/l3 = 0.726
 Mean value RDNS_C3 = 0.634
 Mean value SPHT_K3 = 0.652

User