


DILL_3_SV_14_CRUSH6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\DILL_3_SV_14_CRUSH6K\DILL_3_SV_14_CRUSH6K038.rdf
 Task file: C:\CamsizerXT\CAMSYS\DILL_3_SV_14_CRUSH6K.afg
 Time: 2/12/2015, 16:01, duration 26 min 13 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 91296651, CCD-Z = 1092018
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.959	0.923	0.841	1
#40	#30	0.0	100.0	0.747	0.879	0.785	3
#50	#40	0.0	100.0	0.641	0.724	0.698	160
#60	#50	0.6	100.0	0.877	0.872	0.781	9237
#70	#60	6.2	99.4	0.919	0.900	0.781	155310
#140	#70	82.8	93.2	0.919	0.911	0.755	7219599
PAN	#140	10.4	10.4	0.890	0.919	0.720	257050732



Characteristics

Q3 [%]	x [μm]
10.0	104.9
50.0	150.0
90.0	203.6
SPAN3 =	0.658
U3 =	1.533
Mv3(x) =	150.9 μm
Sigma3(x) =	41.7 μm

Mean value SPHT3 = 0.910
 Mean value Symm3 = 0.909
 Mean value b/l3 = 0.738
 Mean value RDNS_C3 = 0.666
 Mean value SPHT_K3 = 0.678

User