


ELL_02_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\ELL_02_SV_14_PRECRUSH\ELL_02_SV_14_PRECRUSH062.rdf
 Task file: C:\CamsizerXT\CAMSYS\ELL_02_SV_14_PRECRUSH.afg
 Time: 6/23/2015 , 15:18 , duration 7 min 18 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 5466964 , CCD-Z = 70752
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		33.5	100.0	0.746	0.869	0.645	1912
#20	#16	18.5	66.5	0.753	0.864	0.632	4085
#30	#20	15.4	48.0	0.765	0.866	0.628	9007
#40	#30	10.7	32.6	0.779	0.869	0.625	17352
#50	#40	7.3	21.9	0.804	0.873	0.635	34121
#60	#50	2.9	14.6	0.830	0.880	0.652	31306
#70	#60	2.3	11.7	0.851	0.886	0.667	42546
#140	#70	7.0	9.4	0.865	0.895	0.683	495452
PAN	#140	2.4	2.4	0.841	0.913	0.674	13902806



Characteristics

Q3 [%]	x [μm]
10.0	222.2
50.0	882.9
90.0	1993.5
SPAN3 =	2.006
U3 =	4.737
Mv3(x) =	1000.7 μm
Sigma3(x) =	676.4 μm

Mean value SPHT3 = 0.762
 Mean value Symm3 = 0.871
 Mean value b/l3 = 0.617
 Mean value RDNS_C3 = 0.196
 Mean value SPHT_K3 = 0.433

User