


ELL_04_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\ELL_04_SV_14_PRECRUSH\ELL_04_SV_14_PRECRUSH146.rdf
 Task file: C:\CamsizerXT\CAMSYS\ELL_04_SV_14_PRECRUSH.afg
 Time: 6/16/2015 , 10:07 , duration 9 min 1 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 3763329 , CCD-Z = 53235
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		15.6	100.0	0.763	0.875	0.698	1401
#20	#16	19.6	84.4	0.769	0.877	0.675	4665
#30	#20	17.5	64.8	0.782	0.877	0.670	11018
#40	#30	12.3	47.3	0.804	0.876	0.677	22392
#50	#40	10.2	35.0	0.835	0.877	0.695	55099
#60	#50	5.5	24.8	0.867	0.884	0.714	65875
#70	#60	6.1	19.3	0.895	0.896	0.731	128169
#140	#70	12.9	13.2	0.897	0.904	0.722	673575
PAN	#140	0.3	0.3	0.837	0.910	0.673	10926073



Mean value SPHT3 = 0.803
 Mean value Symm3 = 0.881
 Mean value b/l3 = 0.672
 Mean value RDNS_C3 = 0.287
 Mean value SPHT_K3 = 0.545

User