


ENN\_01\_SV\_14\_SPHER\_ROUND

Company:  
 User:  
 Result file: C:\CamsizerXT\CAMDAT\ENN\_01\_SV\_14\_SPHER\_ROUND\ENN\_01\_SV\_14\_SPHER\_ROUND110.rdf  
 Task file: C:\CamsizerXT\CAMSYS\ENN\_01\_SV\_14\_SPHER\_ROUND.afg  
 Time: 5/21/2015, 15:00, duration 5 min 14 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc\_min  
 No. of particles: CCD-B = 1295300, CCD-Z = 0  
 Velocity adaption: no  
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDO
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.370	0.633	0.807	1
#50	#40	0.1	100.0	0.549	0.684	0.654	59
#60	#50	0.9	99.9	0.807	0.829	0.737	1537
#70	#60	7.7	99.0	0.871	0.871	0.746	19756
#140	#70	87.8	91.3	0.917	0.898	0.740	760222
PAN	#140	3.5	3.5	0.929	0.905	0.703	513725



Mean value SPHT3 = 0.905  
 Mean value Symm3 = 0.893  
 Mean value b/l3 = 0.723  
 Mean value RDNS\_C3 = 0.392  
 Mean value SPHT\_K3 = 0.652

User