


ENN_02_SV_14_PRECRUSH

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDAT\ENN_02_SV_14_PRECRUSH\ENN_02_SV_14_PRECRUSH085.rdf
Task file:	C:\CamsizerXT\CAMSYS\ENN_02_SV_14_PRECRUSH.afg
Time:	5/21/2015 , 10:32 , duration 9 min 52 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 4582678 , CCD-Z = 0
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDO
> #16		14.6	100.0	0.738	0.872	0.672	571
#20	#16	10.3	85.4	0.744	0.869	0.665	1418
#30	#20	10.9	75.1	0.764	0.871	0.670	4118
#40	#30	9.4	64.2	0.790	0.868	0.681	10366
#50	#40	11.7	54.8	0.843	0.876	0.717	40189
#60	#50	9.2	43.1	0.884	0.891	0.734	66361
#70	#60	8.7	33.9	0.898	0.897	0.732	104157
#140	#70	22.1	25.2	0.914	0.900	0.731	922899
PAN	#140	3.1	3.1	0.931	0.895	0.715	3432598



Mean value SPHT3 = 0.821
Mean value Symm3 = 0.881
Mean value b/l3 = 0.686
Mean value RDNS_C3 = 0.271
Mean value SPHT_K3 = 0.578

User