


ENN\_02\_SV\_14\_SPHER\_ROUND

Company:  
 User:  
 Result file: C:\CamsizerXT\CAMDAT\ENN\_02\_SV\_14\_SPHER\_ROUND\ENN\_02\_SV\_14\_SPHER\_ROUND099.rdf  
 Task file: C:\CamsizerXT\CAMSYS\ENN\_02\_SV\_14\_SPHER\_ROUND.afg  
 Time: 5/21/2015 , 13:50 , duration 5 min 37 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc\_min  
 No. of particles: CCD-B = 2182481 , CCD-Z = 0  
 Velocity adaption: no  
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDO
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.703	0.696	0.770	1
#50	#40	0.1	100.0	0.649	0.737	0.716	125
#60	#50	1.7	99.9	0.861	0.865	0.756	5424
#70	#60	12.8	98.2	0.900	0.892	0.755	63096
#140	#70	81.5	85.4	0.916	0.898	0.735	1363209
PAN	#140	3.9	3.9	0.920	0.902	0.688	750626



Mean value SPHT3 = 0.905  
 Mean value Symm3 = 0.895  
 Mean value b/l3 = 0.721  
 Mean value RDNS\_C3 = 0.434  
 Mean value SPHT\_K3 = 0.646

User