


ENN_04_SV_14_CRUSH_6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\ENN_04_SV_14_CRUSH_6K\ENN_04_SV_14_CRUSH_6K080.rdf
 Task file: C:\CamsizerXT\CAMSYS\ENN_04_SV_14_CRUSH_6K.afg
 Time: 6/2/2015 , 12:15 , duration 29 min 59 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 51146089 , CCD-Z = 9883378
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.4	100.0	0.842	0.851	0.774	2644
#60	#50	9.2	99.6	0.912	0.900	0.781	104313
#70	#60	21.8	90.4	0.920	0.907	0.762	356734
#140	#70	60.5	68.6	0.920	0.909	0.743	3115526
PAN	#140	8.1	8.1	0.893	0.914	0.709	2875897447



Characteristics

Q3 [%]	x [μm]
10.0	113.0
50.0	184.9
90.0	249.1
SPAN3 = 0.736	
U3 = 1.765	
Mv3(x) = 181.1 μm	
Sigma3(x) = 55.3 μm	

Mean value SPHT3 = 0.911
 Mean value Symm3 = 0.906
 Mean value b/l3 = 0.734
 Mean value RDNS_C3 = 0.646
 Mean value SPHT_K3 = 0.669

User