


ENN_04_SV_14_CRUSH_7K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\ENN_04_SV_14_CRUSH_7K\ENN_04_SV_14_CRUSH_7K080.rdf
 Task file: C:\CamsizerXT\CAMSYS\ENN_04_SV_14_CRUSH_7K.afg
 Time: 6/3/2015, 12:54, duration 31 min 41 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 13927613, CCD-Z = 146212
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.834	0.871	0.854	2
#50	#40	0.1	100.0	0.760	0.809	0.723	95
#60	#50	1.3	99.9	0.872	0.872	0.767	2226
#70	#60	12.6	98.6	0.917	0.902	0.775	32668
#140	#70	73.6	86.0	0.915	0.908	0.748	585731
PAN	#140	12.4	12.4	0.867	0.906	0.699	30581623



Characteristics

Q3 [%]	x [μm]
10.0	95.4
50.0	165.9
90.0	219.1
SPAN3 =	0.745
U3 =	1.864
Mv3(x) =	160.3 μm
Sigma3(x) =	50.4 μm

Mean value SPHT3 = 0.903
 Mean value Symm3 = 0.905
 Mean value b/l3 = 0.733
 Mean value RDNS_C3 = 0.606
 Mean value SPHT_K3 = 0.668

User