


ENN_05_SV_14_CRUSH7K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\ENN_05_SV_14_CRUSH7K\ENN_05_SV_14_CRUSH7K138.rdf
 Task file: C:\CamsizerXT\CAMSYS\ENN_05_SV_14_CRUSH7K.afg
 Time: 6/15/2015 , 15:05 , duration 27 min 32 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 75049923 , CCD-Z = 929627
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.0	100.0	0.714	0.767	0.732	87
#60	#50	0.5	100.0	0.863	0.864	0.779	3678
#70	#60	5.6	99.5	0.912	0.897	0.782	73434
#140	#70	80.7	93.9	0.917	0.909	0.758	3685874
PAN	#140	13.2	13.2	0.879	0.912	0.710	135584034



Characteristics

Q3 [%]	x [μm]
10.0	95.2
50.0	147.0
90.0	201.4
SPAN3 =	0.722
U3 =	1.660
Mv3(x) =	147.1 μm
Sigma3(x) =	43.7 μm

Mean value SPHT3 = 0.906
 Mean value Symm3 = 0.907
 Mean value b/l3 = 0.739
 Mean value RDNS_C3 = 0.625
 Mean value SPHT_K3 = 0.682

User