


ENN_06_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\ENN_06_SV_14_PRECRUSH\ENN_06_SV_14_PRECRUSH133.rdf
 Task file: C:\CamsizerXT\CAMSYS\ENN_06_SV_14_PRECRUSH.afg
 Time: 6/15/2015, 8:48, duration 5 min 40 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 5533171, CCD-Z = 2100140
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		26.5	100.0	0.758	0.873	0.689	2173
#20	#16	26.6	73.5	0.755	0.870	0.652	5463
#30	#20	16.7	46.9	0.756	0.869	0.633	9061
#40	#30	9.4	30.2	0.772	0.869	0.635	14388
#50	#40	5.8	20.8	0.804	0.869	0.655	26383
#60	#50	2.4	15.0	0.833	0.873	0.674	25362
#70	#60	2.2	12.6	0.858	0.880	0.689	39754
#140	#70	9.3	10.4	0.896	0.899	0.712	603113
PAN	#140	1.1	1.1	0.871	0.909	0.656	621602249



Characteristics

Q3 [%]	x [μm]
10.0	206.4
50.0	890.2
90.0	1453.5
SPAN3 = 1.401	
U3 = 4.919	
Mv3(x) = 866.9 μm	
Sigma3(x) = 450.0 μm	

Mean value SPHT3 = 0.770
 Mean value Symm3 = 0.874
 Mean value b/l3 = 0.643
 Mean value RDNS_C3 = 0.238
 Mean value SPHT_K3 = 0.484

User