


ENN_07_SV_14_CRUSH6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\ENN_07_SV_14_CRUSH6K\ENN_07_SV_14_CRUSH6K083.rdf
 Task file: C:\CamsizerXT\CAMSYS\ENN_07_SV_14_CRUSH6K.afg
 Time: 5/20/2015 , 16:25 , duration 19 min 35 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 38712974 , CCD-Z = 0
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDO
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.1	100.0	0.703	0.745	0.725	273
#60	#50	1.7	99.9	0.885	0.876	0.779	15082
#70	#60	16.3	98.2	0.920	0.901	0.776	229740
#140	#70	73.2	81.9	0.923	0.905	0.741	2628160
PAN	#140	8.7	8.7	0.926	0.889	0.699	35839718



Mean value SPHT3 = 0.915
 Mean value Symm3 = 0.902
 Mean value b/l3 = 0.733
 Mean value RDNS_C3 = 0.513
 Mean value SPHT_K3 = 0.671

User