


ENN\_07\_SV\_14\_PRECRUSH

Company:  
 User:  
 Result file: C:\CamsizerXT\CAMDAT\ENN\_07\_SV\_14\_PRECRUSH\ENN\_07\_SV\_14\_PRECRUSH049.rdf  
 Task file: C:\CamsizerXT\CAMSYS\ENN\_07\_SV\_14\_PRECRUSH.afg  
 Time: 5/14/2015, 15:04, duration 10 min 49 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc\_min  
 No. of particles: CCD-B = 3097683, CCD-Z = 48991  
 Velocity adaption: no  
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		8.0	100.0	0.740	0.880	0.718	704
#20	#16	11.9	92.0	0.756	0.880	0.715	2655
#30	#20	13.6	80.1	0.779	0.875	0.722	8638
#40	#30	13.9	66.5	0.806	0.872	0.729	25028
#50	#40	14.6	52.6	0.841	0.873	0.732	74867
#60	#50	9.0	38.0	0.881	0.885	0.743	101891
#70	#60	10.0	29.0	0.907	0.898	0.747	184589
#140	#70	18.7	19.0	0.910	0.907	0.726	844969
PAN	#140	0.3	0.3	0.874	0.913	0.679	6366563



Mean value SPHT3 = 0.828  
 Mean value Symm3 = 0.884  
 Mean value b/l3 = 0.715  
 Mean value RDNS\_C3 = 0.329  
 Mean value SPHT\_K3 = 0.649

User