


ENN_08_SV_14_CRUSH6K

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDAT\ENN_08_SV_14_CRUSH6K\ENN_08_SV_14_CRUSH6K134.rdf
Task file:	C:\CamsizerXT\CAMSYS\ENN_08_SV_14_CRUSH6K.afg
Time:	6/15/2015 , 10:36 , duration 26 min 1 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 47149221 , CCD-Z = 686532
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.0	100.0	0.670	0.733	0.724	137
#60	#50	0.9	100.0	0.880	0.874	0.781	8889
#70	#60	12.4	99.1	0.924	0.906	0.784	182534
#140	#70	78.6	86.7	0.922	0.912	0.753	3306043
PAN	#140	8.1	8.1	0.880	0.915	0.714	85456687



Mean value SPHT3 = 0.913
Mean value Symm3 = 0.910
Mean value b/l3 = 0.740
Mean value RDNS_C3 = 0.655
Mean value SPHT_K3 = 0.683

User