


ENN_08_SV_14_CRUSH7K

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDAT\ENN_08_SV_14_CRUSH7K\ENN_08_SV_14_CRUSH7K136.rdf
Task file:	C:\CamsizerXT\CAMSYS\ENN_08_SV_14_CRUSH7K.afg
Time:	6/15/2015 , 11:35 , duration 25 min 47 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 84000117 , CCD-Z = 1129748
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.949	0.894	0.792	2
#50	#40	0.0	100.0	0.708	0.758	0.746	169
#60	#50	0.8	100.0	0.881	0.875	0.783	8505
#70	#60	11.1	99.2	0.924	0.906	0.785	180355
#140	#70	77.5	88.1	0.923	0.912	0.755	3673688
PAN	#140	10.6	10.6	0.882	0.912	0.717	127186430



Mean value SPHT3 = 0.913
Mean value Symm3 = 0.909
Mean value b/l3 = 0.741
Mean value RDNS_C3 = 0.650
Mean value SPHT_K3 = 0.686

User