


ENN\_08\_SV\_14\_SPHERE\_ROUND

Company:  
 User:  
 Result file: C:\...zerXT\CAMDAT\ENN\_08\_SV\_14\_SPHERE\_ROUND\ENN\_08\_SV\_14\_SPHERE\_ROUND131.rdf  
 Task file: C:\CamsizerXT\CAMSYS\ENN\_08\_SV\_14\_SPHERE\_ROUND.afg  
 Time: 6/15/2015, 9:16, duration 6 min 4 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc\_min  
 No. of particles: CCD-B = 1766217, CCD-Z = 22684  
 Velocity adaption: no  
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.1	100.0	0.614	0.699	0.699	120
#60	#50	1.1	99.9	0.849	0.853	0.761	3783
#70	#60	12.9	98.8	0.910	0.895	0.772	68008
#140	#70	84.4	85.9	0.907	0.907	0.740	1226916
PAN	#140	1.5	1.5	0.834	0.908	0.630	5266842



Mean value SPHT3 = 0.899  
 Mean value Symm3 = 0.903  
 Mean value b/l3 = 0.729  
 Mean value RDNS\_C3 = 0.605  
 Mean value SPHT\_K3 = 0.659

User