


ENN_10_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\ENN_10_SV_14_PRECRUSH\ENN_10_SV_14_PRECRUSH080.rdf
 Task file: C:\CamsizerXT\CAMSYS\ENN_10_SV_14_PRECRUSH.afg
 Time: 5/22/2015, 13:09, duration 6 min 57 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 1833649, CCD-Z = 1640194
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		36.7	100.0	0.724	0.872	0.656	1813
#20	#16	19.4	63.3	0.745	0.871	0.645	3598
#30	#20	14.1	43.9	0.761	0.872	0.646	7132
#40	#30	8.7	29.8	0.784	0.872	0.656	12542
#50	#40	6.2	21.1	0.814	0.874	0.671	25868
#60	#50	2.6	14.9	0.840	0.876	0.687	25290
#70	#60	2.2	12.3	0.861	0.880	0.700	35232
#140	#70	9.2	10.1	0.903	0.902	0.724	641889
PAN	#140	0.9	0.9	0.916	0.930	0.710	318096869



Characteristics

Q3 [%]	x [μm]
10.0	209.6
50.0	953.5
90.0	1966.6
SPAN3 = 1.843	
U3 = 5.336	
Mv3(x) = 1047.0 μm	
Sigma3(x) = 712.1 μm	

Mean value SPHT3 = 0.761
 Mean value Symm3 = 0.875
 Mean value b/l3 = 0.644
 Mean value RDNS_C3 = 0.239
 Mean value SPHT_K3 = 0.485

User