


ENN_10_SV_14_SPHER_ROUND

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDAT\ENN_10_SV_14_SPHER_ROUND\ENN_10_SV_14_SPHER_ROUND051.rdf
Task file:	C:\CamsizerXT\CAMSYS\ENN_10_SV_14_SPHER_ROUND.afg
Time:	5/22/2015 , 14:30 , duration 5 min 9 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 400782 , CCD-Z = 10166
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.2	100.0	0.534	0.695	0.644	44
#30	#20	20.1	99.8	0.769	0.858	0.698	10239
#40	#30	68.2	79.7	0.794	0.874	0.670	67882
#50	#40	11.0	11.5	0.764	0.876	0.557	19785
#60	#50	0.3	0.5	0.644	0.862	0.394	1070
#70	#60	0.1	0.2	0.622	0.859	0.399	346
#140	#70	0.1	0.1	0.790	0.897	0.644	2528
PAN	#140	0.0	0.0	0.897	0.924	0.784	5505340



Mean value SPHT3 = 0.773
Mean value Symm3 = 0.869
Mean value b/l3 = 0.638
Mean value RDNS_C3 = 0.313
Mean value SPHT_K3 = 0.478

User