


ENN_11_SV_14_CRUSH_5K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\ENN_11_SV_14_CRUSH_5K\ENN_11_SV_14_CRUSH_5K067.rdf
 Task file: C:\CamsizerXT\CAMSYS\ENN_11_SV_14_CRUSH_5K.afg
 Time: 5/26/2015 , 12:17 , duration 31 min 2 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 49433340 , CCD-Z = 644534
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.797	0.866	0.625	6
#50	#40	0.0	100.0	0.687	0.760	0.684	72
#60	#50	0.5	100.0	0.845	0.851	0.768	3120
#70	#60	5.9	99.5	0.910	0.895	0.779	65691
#140	#70	83.1	93.6	0.921	0.912	0.760	2956513
PAN	#140	10.5	10.5	0.881	0.914	0.716	121712993



Mean value SPHT3 = 0.911
 Mean value Symm3 = 0.909
 Mean value b/l3 = 0.743
 Mean value RDNS_C3 = 0.647
 Mean value SPHT_K3 = 0.691

User